

## CaroTex 2 — Natural Rubber

### TECHNICAL DATA

Maximum recommended  
temperature: 200° F

Maximum recommended  
pressure: 300 P.L.I.

Recommended thickness:  
3/4" to 1"

Hardness range: 30 to 95 Shore A  
durometer

### CHEMICAL RESISTANCE

Good resistance to caustics,  
acids, peroxide and usual  
finishing agents. Not resistant  
to oils or other hydrocarbons  
such as varsol, toluene, naphtha  
and xylene.

### APPLICATIONS

Carotex 2 is a very rugged  
cover with excellent abrasion  
resistance. It is recommended  
for use in caustic pads; open  
width washers, rope washers  
and bleacher squeeze roll  
operations.

A Carolina Rubber Rolls  
Product Engineer can best  
explain to you the full  
characteristics of CaroTex 2.

*Carolina Rubber Rolls*<sup>™</sup>  
HBD INDUSTRIES, INC.

1820 S. BOUNDARY STREET  
SALISBURY, NC 28144-6747

**800/438-2312**

Fax:  
**704/633-3880**

E-mail:  
[custserv@carolinarubberrolls.com](mailto:custserv@carolinarubberrolls.com)

Visit our websites at  
[www.carolinarubberrolls.com](http://www.carolinarubberrolls.com)  
[www.hbdthermoid.com](http://www.hbdthermoid.com)  
[www.hbdindustries.com](http://www.hbdindustries.com)

*HBD Industries... Leadership Through Technology*

