

CaroTex 3 — Viton®

TECHNICAL DATA

Maximum recommended temperature: 400° F (continuous), 500° F (intermittent)

Maximum recommended pressure: 200 P.L.I.

Recommended thickness: 1/4" to 3/4"

Hardness range: 60 to 90 Shore A durometer

CHEMICAL RESISTANCE

Excellent resistance to most mineral acids, strong oxidizing agents, hydrocarbons, oils, and chlorinated solvents. Poor resistance to acetone, MEK and other ketones.

APPLICATIONS

The outstanding heat, chemical and solvent resistance of CaroTex 3 recommends it for applications requiring solvent scouring, coating and dyeing, for high heat shrink proofing, and/or industrial acid coatings. As an exotic, all purpose roll covering, CaroTex 3 is often used where no other covering will work.

A Carolina Rubber Rolls Product Engineer can best explain to you the full characteristics of CaroTex 3.

Carolina Rubber Rolls™
HBD INDUSTRIES, INC.

1820 S. BOUNDARY STREET
SALISBURY, NC 28144-6747

800/438-2312

Fax:
704/633-3880



HBD/THS-19324-D
Printed in U.S.A.

E-mail: custserv@carolinarubberrolls.com

Visit our websites at
www.carolinarubberrolls.com
www.hbdthermoid.com
www.hbdindustries.com

HBD Industries... Leadership Through Technology