


### BLACK MONOFILAMENT BELTING



<b>Description:</b>	[size"]x3P MONO135 BLK NAT BBxBB (S30) (3) PACK-EZ
<b>Product Number</b>	24303350722 24303350602 24303350482
<b>Product Construction</b>	Bare X Bare (Black Natural Rubber on Mono/Poly Fabric)
<b>Color</b>	Black
<b>Compound Formulation</b>	Natural
<b>Fabric</b>	Monofilament/Polyester
<b>Nominal Overall Gauge</b>	0.131 ± 0.020 in (3.3 ± 0.5 mm)
<b>Nominal Weight</b>	0.81 ±10% lbs./ft <sup>2</sup> (3.77 ±10% kg/m <sup>2</sup> )
<b>Rated Working Tension</b>	135 lbs./inch (23.7 N/mm)
<b>Top Cover Surface</b>	Bare
<b>Bottom Cover Surface</b>	Bare
<b>Minimum Pulley Diameter</b>	3 in (76 mm)
<b>Temperature Range</b>	-20° to +180°F (-28° to +82°C)
<b>Special Standards</b>	ASTM D378 Flame Test – 60 seconds max
<b>Cover Coefficient of Friction</b>	0.18 max Steel (0.20 max Cardboard)
<b>Bottom Coefficient of Friction, Steel</b>	0.18 max Steel (0.20 max Cardboard)
<b>Available Width(s)</b>	72", 59.5", 47.5"
<b>Typical Applications</b>	<ul style="list-style-type: none"> <li>• Package Handling</li> <li>• Warehouse and distribution center package and tote handling</li> </ul>
<b>Benefits</b>	<ul style="list-style-type: none"> <li>• Special fabric for low coefficient friction</li> <li>• Great tracking properties for slider bed usages</li> <li>• Fire Resistant compounds to ASTM D378 Flame Test – 60 seconds max</li> </ul>

Phone: 800-543-8070

Email: [info@thermoid.com](mailto:info@thermoid.com)

[www.thermoid.com](http://www.thermoid.com)

HBD/Thermoid is not responsible for possible errors in catalogues, brochures, websites and other materials, and may change such information without notice. HBD Thermoid reserves the right to modify its products without notice, including products already on order, as long as the modified product meets any agreed-upon specifications. All trademarks in this material are the property of the HBD Industries Inc., or its subsidiaries.