


### HOT 'N COLD – WHITE BUTYL BELTING



<b>Description:</b>	72"x3P APT105 WHT BUTYL 1/32xFS (S10) (1,2) HOT/COLD
<b>Product Number</b>	24243721722
<b>Product Construction</b>	Smooth X Friction (White Butyl on Treated Polyester Fabric)
<b>Color</b>	White
<b>Compound Formulation</b>	Butyl
<b>Fabric</b>	Treated Polyester
<b>Nominal Overall Gauge</b>	0.112 ± 0.020 in (2.8 ± 0.50 mm)
<b>Nominal Weight</b>	0.75 ±10% lbs./ft <sup>2</sup> (3.66 ±10% kg/m <sup>2</sup> )
<b>Rated Working Tension</b>	105 lbs./inch (18 N/mm)
<b>Top Cover Surface</b>	Smooth
<b>Bottom Cover Surface</b>	Friction
<b>Minimum Pulley Diameter</b>	2 in (4 below 0 °F); 51 mm (101 below -18°C)
<b>Temperature Range</b>	-65° to +300°F (-54° to +149°C)
<b>Special Standards</b>	USDA/FDA Approved
<b>Cover Coefficient of Friction</b>	1.0 nominal Steel (1.0 nominal Cardboard)
<b>Bottom Coefficient of Friction</b>	0.30 to 0.35 Steel (0.35 to 0.40 Cardboard)
<b>Available Width(s)</b>	72"
<b>Typical Applications</b>	<ul style="list-style-type: none"> <li>• Hot Food</li> <li>• Dairies or bakeries (temperature conditions)</li> <li>• Meats, poultry and bakery</li> <li>• Fruit and vegetable processing</li> <li>• Frozen foods (sub-zero temperatures)</li> </ul>
<b>Benefits</b>	<ul style="list-style-type: none"> <li>• Butyl compound is designed for temperatures from -65°F to +300°F</li> <li>• Polyester fabric is low stretch and moisture resistant</li> </ul>

Phone: 800-543-8070

Email: [info@thermoid.com](mailto:info@thermoid.com)

[www.thermoid.com](http://www.thermoid.com)

HBD/Thermoid is not responsible for possible errors in catalogues, brochures, websites and other materials, and may change such information without notice. HBD Thermoid reserves the right to modify its products without notice, including products already on order, as long as the modified product meets any agreed-upon specifications. All trademarks in this material are the property of the HBD Industries Inc., or its subsidiaries.